

Pre-Paint Preparation

PAINTERS Caulk

Easy, Water Cleanup / Paints & Stains Easily / Watertight Seal

Titebond® Painters Caulk is an interior use, latex caulk that repairs cracks in plaster/ drywall and fills gaps around wood trim, moldings, mantels and baseboards. It de-aired for a smooth, uniform bead that extrudes and tools easily leaving no residual odor behind. It is a mildew resistant formula that contains no plasticizers or phthalates.

25 YEAR WARRANTY

Ideal For

Interior Applications Like: Sealing Joints /
Repairing Cracks / Filling Gaps

Seals

Wood / Metal / Glass / Masonry / Aluminum /
Brick / Most Common Building Materials

Ultra Low VOC

VOC-compliant in all 50 states

Weather Resistant

Produces long-lasting weather-tight seals

Paintable

May be painted with a water-based (latex-based)
paint 2-4 hours after application

Wide Temperature Application Range

40°F - 120°F



Titebond®
THE PRO'S ADVANTAGE

Ordering/Sku Information

Size/Color	Part Number	UPC	Case UPC	Weight	Units Per Package	Packages Per Pallet
10.1 Oz. Cartridge / White	7301	037083073010	10037083073017	15.01 lbs.	12	108

Physical & Chemical Properties

- **Type:** Latex
- **Calculated VOC:** <50 g/L (<1.5%)
- **Weight per gallon:** 13.5 lbs.
- **Tooling time:** 10-15 minutes
- **Full cure:** 3-7 days*
- **Freeze thaw stability:** Stable
- **Flashpoint:** Solvent free/Not applicable
- **Application temperature:** Above 40°F (4°C)
- **Joint movement capability:** Flexible
- **Storage life:** 24 months in a dry location at or below 75°F
- **Coverage:** 31 linear ft. at a 1/4" bead
- **Paintable:** 2-4 hours
- **Tack-free time:** 2-3 hours
- **Solids:** 82%
- **Cleanup:** Clean uncured material with water. After curing, excess sealant must be cut or scraped away.

* Cure will be affected by joint size, configuration and environmental conditions.

Specifications

Complies with the following requirements:

- ASTM C834 Type OP Grade -18°C

Application

Titebond® Painters Caulk comes ready to use. Surfaces must be clean and free of any material that may prevent adequate adhesion. Properly designed joint not to exceed 1/2" in depth. Cut tip at 45° angle for 1/8" to 1/2" bead and place in cartridge gun. Force caulk into clean joint. If necessary, smooth bead immediately. It is the sole responsibility of the user to thoroughly test any proposed use with all substrates to determine project suitability.

Limitations

Not designed for continuous submersion or use below the waterline. Air, caulk and surface temperature should be above 40°F. Cure time is dependent upon ambient conditions including temperature and humidity. The caulk should be dry to the touch and ready to paint in 2-4 hours with a water-based (latex-based) paint. For other paint types, a compatibility test is recommended. It is highly recommended to use backing material. For best results, store in a dry location at or below 75°F. For questions, please call our Help Line 1.800.347.4583 or visit us at Titebond.com.

25 Year Limited Warranty: If not satisfied with product performance when used as directed, return container and proof of purchase to Franklin International, Inc. for replacement of product. Liability is limited to product replacement only.



Visit Titebond.com for the most up-to-date product information.

Franklin International



Columbus, Ohio 43207 614.443.0241 Technical Service 1.800.347.4583 © 2020 00711_4861LN FF1013